



## Material data sheet – FlexLine

---

### EOS Titanium TiCP

EOS Titanium TiCP is a titanium alloy powder intended for processing on EOS DMLS™ machines.

This document provides information and data for parts built using:

- EOS Titanium TiCP grade 2 powder (EOS art.-no. 9011-0036)
- EOS DMLS™ EOS M404 system
  - HSS blade (2200-4073)
  - Argon atmosphere
  - IPCM extra sieving module with 63 µm mesh (9044-0032) recommended
- EOSYSTEM:
  - EOSPRINT v 1.5 (Build9) or higher
  - HCS v 2.5.22 or higher
- EOS Parameter set: TiCP\_030\_FlexM404\_100

### Description

The parts built with EOS Titanium TiCP grade 2 powder have chemical composition corresponding to ASTM F67. The parts have good strength-to-weight ratio, corrosion resistance and ductility. Parts built with EOS Titanium TiCP grade 2 powder can be machined, shot-peened and polished in as-built and heat treated states. Due to the layer-wise building method, the parts have a certain anisotropy.

### Quality Assurance

The quality of the EOS Titanium TiCP grade 2 powder lots is ensured by the Quality Assurance procedures. The procedures include sampling (ASTM B215), PSD analysis (DIN ISO 13320), and chemical analyses. The results of the quality assurance tests are given in the lot specific Mill Test Certificates (MTC).

## Material data sheet – FlexLine

### Technical Data

#### Powder properties

The chemical composition of the powder (wt-%):

Material composition			
	Element	Min	Max
	N	-	0.03
	C	-	0.08
	H	-	0.015
	Fe	-	0.30
	O	-	0.25
	Ti		Bal.

#### Max. particle size

> 63µm Max. 0.3 wt%

#### General process data

Layer thickness	30 µm
Volume rate [1]	5.0 mm <sup>3</sup> /s (18.0 cm <sup>3</sup> /h) 1.1 in <sup>3</sup> /h

[1] The volume rate is a measure of build speed during laser exposure of the skin area. The total build speed depends on this volume rate and many other factors such as exposure parameters of contours, supports, up and downskin, recoating time, Home-In or LPM settings.

## Material data sheet – FlexLine

### Physical and chemical properties of parts

Part density [2]	Approx. 4.5 g/cm <sup>3</sup> Approx. 0.163 lb/in <sup>3</sup>
Min. wall thickness [3]	Approx. 0.3 – 0.4 mm Approx. 0.012 – 0.016 inch
Surface roughness after shot peening [4]	Ra < 10 μm; Rz < 55 μm Ra < 0.4 10 <sup>-3</sup> inch Rz < 2.2 10 <sup>-3</sup> inch

[2] Weighing in air and water according to ISO 3369.

[3] Mechanical stability is dependent on geometry (wall height etc.) and application.

[4] Measurement according to ISO 4287. Due to the layerwise building the roughness strongly depends on the orientation of the surface, for example sloping and curved surfaces exhibit a stair-step effect.

### Tensile data at room temperature [5,6]

	Heat treated [7]	
	Horizontal	Vertical
Ultimate tensile strength, Rm	570 MPa	560 MPa
Yield strength, Rp0.2	430 MPa	430 MPa
Elongation at break A [8]	24 %	24 %
Reduction of area, Z	52 %	52 %

[5] Tensile testing according to ISO 6892-1 A14, proportional test pieces, diameter of the neck area 5 mm (0.2 inch), original gauge length 20 mm (0,79 inch).

[6] The numbers are average values determined from samples with horizontal and vertical orientation respectively

[7] Specimens were heat treated at 700 °C for 1.5 hours in argon inert atmosphere.

[8] Values are averaged and subject to variations depending on process conditions



## Material data sheet – FlexLine

---

### Abbreviations

Min.	Minimum
Max.	Maximum
Approx.	Approximately
Wt.	Weight

The quoted values refer to the use of this material with above specified type of EOS DMLS system, EOSYSTEM software version, parameter set and operation in compliance with parameter sheet and operating instructions. Part properties are measured with specified measurement methods using defined test geometries and procedures. Further details of the test procedures used by EOS are available on request. Any deviation from these standard settings may affect the measured properties.

The data correspond to EOS knowledge and experience at the time of publication and they are subject to change without notice as part of EOS' continuous development and improvement processes.

EOS does not warrant any properties or fitness for a specific purpose, unless explicitly agreed upon. This also applies regarding any rights of protection as well as laws and regulations.

EOS<sup>®</sup>, EOSINT<sup>®</sup>, DMLS<sup>®</sup>, DirectTool<sup>®</sup> and DirectPart<sup>®</sup> are registered trademarks of EOS GmbH.

© 2017 EOS GmbH – Electro Optical Systems. All rights reserved.