

POLYMER SOLUTIONS

PA 2200 CarbonReduced Speed

Material Data Sheet

PA 2200 CARBONREDUCED SPEED

Product Description

PA 2200 CarbonReduced, based on polyamide 12, offers a wide range of applications thanks to its very balanced property profile and is the most proven material on the market.

PA 2200 CarbonReduced is an EOS Responsible Product. It combines a heavily reduced CO₂e footprint with the well-known technical properties of PA 2200.

The Speed parameter set applies the classic 150 µm layer thickness which is popular and widespread on the market due to its allround qualities. This parameter set offers slightly higher surface quality than TopSpeed.

MAIN CHARACTERISTICS

- 100% proven quality and 45% less CO₂e
- Balanced property profile
- Multipurpose material

TYPICAL APPLICATIONS

- Production equipment like grippers, jigs and fixtures
- Surgery cutting guides and bone models for the medical industry
- Eye wear in the consumer goods industry
- Spare parts like brackets or covers, e.g., in the automotive industry
- Functional parts for prototyping, that include hinges or threads

MECHANICAL PROPERTIES	DRY / CONDITIONED	UNIT	TEST STANDARD
Tensile Modulus			ISO 527-1/-2
X Orientation	1600 / -	MPa	
Y Orientation	1600 / -	MPa	
Z Orientation	1550 / -	MPa	
Tensile Strength			ISO 527-1/-2
X Orientation	48 / -	MPa	
Y Orientation	48 / -	MPa	
Z Orientation	42 / -	MPa	
Nominal Strain at Break			ISO 527-1/-2
X Orientation	18 / -	%	
Y Orientation	18 / -	%	
Z Orientation	4 / -	%	
Shore D Hardness			ISO 7619-1
X Orientation	75 / -	-	

OTHER PROPERTIES	VALUE	UNIT	TEST STANDARD
Powder Color	white	-	-
Components Color	white	-	-

HEADQUARTERS

EOS GmbH
Electro Optical Systems

Robert-Stirling-Ring 1
82152 Krailling / Munich
Germany

Tel.: +49 89 893 36-0
Email: info@eos.info
URL: www.eos.info

This powder has not been developed, tested or certified as a medical device according to Directive 93/42/EEC (MDD) or Regulation (EU) 2017/745 (MDR) and is not intended to be used as a medical device, in particular for the purposes specified in Art. 2 No. 1 MDR. Insofar as you intend to use the powder as raw material for the manufacture of pharmaceutical products or medical devices (e.g. as raw material which as a material must meet the requirements of Annex 1, Chapter II MDR), the responsibility and liability for all analyses, tests, evaluations, procedures, risk assessments, conformity assessments, approval and certification procedures as well as for all other official and regulatory measures required for this purpose shall lie solely with you both with regard to the pharmaceutical product and/or medical device manufactured by you and with regard to the properties, suitability, testing, evaluation, risk assessment, other requirements for use of the powder as raw material. In this respect, the limitations of liability pursuant to our General Terms and Conditions and the system sales or material contracts shall apply.

Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein. This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

The achievement of certain part properties as well as the assessment of the suitability of this material for a specific purpose is the sole responsibility of the user. Any information given herein is subject to change without notice.