



EOS ALUMINIUM ALSI10MG

Good Strength & Dynamic Load Bearing Capacity

EOS Aluminium AlSi10Mg is a widely used alloy that combines light weight and good mechanical properties. Different heat treatments can be applied to modify properties for example to increase ductility and conductivity. The material has good thermal and electrical conductivity especially after heat treatment. In addition, gas tight parts can be manufactured with EOS Aluminium AlSi10Mg.

MAIN CHARACTERISTICS

- ightarrow Good strength, hardness and dynamic properties
- \rightarrow High corrosion resistance
- ightarrow Good thermal and electrical conductivity
- ightarrow Properties can be modified with heat treatments

Download Process Data Sheet (PDF) \rightarrow



TYPICAL APPLICATIONS

- → General engineering components and parts subject to high loads
- ightarrow Lightweight designs
- ightarrow Aerospace and automotive components
- → Substitution of cast AlSi10Mg parts


The EOS Quality Triangle

EOS uses an approach that is unique in the AM industry, taking each of the three central technical elements of the production process into account: the system, the material and the process. The data resulting from each combination is assigned a Technology Readiness Level (TRL) which makes the expected performance and production capability of the solution transparent.

EOS incorporates these TRLs into the following two categories:

- → Premium products (TRL 7-9): offer highly validated data, proven capability and reproducible part properties.
- → Core products (TRL 3 and 5): enable early customer access to newest technology still under development and are therefore less mature with less data.

All of the data stated in this material data sheet is produced according to EOS Quality Management System and international standards



POWDER PROPERTIES

The chemical composition of the EOS Aluminium AlSi10Mg powder is in compliance with the DIN EN 1706 (EN AC—43000) and ASTM F3318 standard.

Powder Chemical Composition (wt.-%)

Element	Min.	Max.
Al		Balance
Si	9.0	11.0
Fe	0.0	0.55
Cu	0.0	0.05
Mn	0.0	0.45
Mg	0.2	0.45
Ni	0.0	0.05
Zn	0.0	0.1
Pb	0.0	0.03
Sn	0.0	0.05
Ti	0.0	0.15

SEM micrograph of EOS Aluminium AlSi10Mg powder

Powder Particle Size

GENERIC PARTICLE SIZE DISTRIBUTION	25 - 70 μm
------------------------------------	------------

HEAT TREATMENT

Description

EOS T6 Heat Treatment

EOS has developed an AM optimized heat treatment procedure that is 40% shorter than conventional T6 heat treatment procedures.

Solution annealing 30 min @ 530 °C, water quench. Artificial aging 6 h @ 165 °C, cooling in air. Parts to preheated oven. Maximum overheating 5 °C. Delay between SA and quenching maximum 30 s. Oven type & configuration may have impact on the mechanical properties. For complex and massive parts uniform heating and cooling needs to be arranged.

EOS T6 treatment is recommended to obtain controlled mechanical properties and lower variation in mechanical values (for example in long build jobs if heat transfer from parts is limited by low amount of support and after stress relief heat treatment). An increase in porosity due to heat treatment is possible. A more detailed description of heat treatment is available upon request.


Steps

Solution Annealing

30 minutes in 530 °C followed by immediate quenching to water.

Aging

Artificial aging of 6 hours in 165 °C followed by cooling in air.



HEADQUARTERS

EOS GmbH Electro Optical Systems Robert-Stirling-Ring 1 82152 Krailling / Munich Germany Tel.: +49 89 893 36-0 Email: info@eos.info URL: www.eos.info

This powder has not been developed, tested or certified as a medical device according to Directive 93/42/EEC (MDD) or Regulation (EU) 2017/745 (MDR) and is not intended to be used as a medical device, in particular for the purposes specified in Art. 2 No. 1 MDR. Insofar as you intend to use the powder as raw material for the manufacture of pharmaceutical products or medical devices (e.g. as raw material which as a material must meet the requirements of Annex 1, Chapter II MDR), the responsibility and liability for all analyses, tests, evaluations, procedures, risk assessments, conformity assessments, approval and certification procedures as well as for all other official and regulatory measures required for this purpose shall lie solely with you both with regard to the pharmaceutical product and/or medical device manufactured by you and with regard to the properties, suitability, testing, evaluation, risk assessment, other requirements for use of the powder as raw material. In this respect, the limitations of liability pursuant to our General Terms and Conditions and the system sales or material contracts shall apply.

Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein. This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

The achievement of certain part properties as well as the assessment of the suitability of this material for a specific purpose is the sole responsibility of the user. Any information given herein is subject to change without notice.

Status as of 04.11.2025. Subject to technical modifications. EOS is certified according to ISO 9001.

EOS®, Additive Minds® Alumide®, AMQ®, CarbonMide®, DirectMetal®, DMLS®, EOSAME®, EOSINT®, EOSIZE®, EOSPACE®, EOSPRINT®, EOSTATE®, EOSTYLE®, FORMIGA®, LaserProFusion®, PA 2200®, PrimeCast® and PrimePart® are registered trademarks of EOS GmbH Electro Optical Systems in some countries. For more information visit www.eos.info/trademarks.